

In the Claims:

Please amend Claim 1. The changes in this Claim are shown with ~~strikethroughs~~ for deleted matter and underlines for added matter. A complete listing of the claims, with proper claim identifiers, is set forth below.

1. (Currently Amended) A union fabric obtained by co-weaving:

(A)a fiber yarn (A) that has, as a principal component, a halogen-containing flame resistant fiber including 25 to 50 parts by weight of an antimony compound ~~25 parts to 50 parts in~~ 100 parts by weight of an acrylic based copolymer ~~100 parts consisting of~~ 30% to 70% by weight of acrylonitrile ~~30% to 70% by weight,~~ 30% to 70% by weight of a halogen-containing vinyl based monomer ~~30% to 70% by weight and~~ 0% to 10% by weight of a vinyl based monomer copolymerizable therewith ~~0% to 10% by weight; and~~

(B)a compound yarn (B) consisting of a cellulosic fiber (b-1) and a fiber melting at temperatures of 200 degrees C to 400 degrees C (b-2);

said fiber yarn (A) comprising 30% to 70% by weight of the union fabric and said compound yarn (B) comprising 70% to 30% by weight of the union fabric wherein the total weight of the fabric is 100%;

said co-woven fabric being flame resistant to an extent sufficient to pass France's Class M1 in the NF-P 92-503 Combustion Test.

2. (Original) The flame resistant union fabric according to Claim 1, wherein the cellulosic fiber (b-1) is at least one kind selected from a group consisting of cotton, hemp, rayon, polynosic, cupra, acetate, and triacetate.